

SELF-ADHESIVE SBS MEMBRANE

Description

Self-Adhesive membrane **Aquaproof SBS** is a self-adhesive bituminous waterproofing sheet with non-protected surface. Composed of self-adhesive SBS polymer bitumen with an upper surface finish of a high-density polyethylene film (HDPE) and a lower surface finish of siliconized release film. It conforms to the requirement of BS 8102.

Uses

Aquaproof SBS is used for the waterproofing and damp proofing of underground walls, basement raft, tunnels, substructures and inverted roofs under tiles.

Advantages

Watertight - resistance to hydrostatic head of water.

Crack Bridging properties due to high compound elongation - allows membrane to accommodate movements in the building structure.

Excellent mechanical properties in all directions (tear strength and tensile strength, puncture and impact resistance) due to the high density polyethylene film (HDPE) finish.

Elastic behaviour (good memory and recovery).

Elastomeric and self-healing, minor perforation will automatically heal.

Cold applied, easy and fast application, no torch is necessary.

Total flexibility of the material to apply to complex geometries & perfect accommodation to the support.

Excellent adhesion to the primed support.

Controlled thickness during factory production ensuring constant error-free site application.

High durability of the waterproofing due to the SBS elastomer compound of the membrane.

High chemical, oxidation & microbiological resistance.

Technical Data

Properties	Value	Standard
Thickness	1.5 ± 0.1 mm	-----
Hydrostatic Pressure Resistance	≥4 bar (40m) No Leakage	BS EN 12390 (Part 8)
Tensile Strength, Longitudinal	≥1.3 N/mm ²	ASTM D5147 / ASTM D882
Tensile Strength, Transversal	≥1.2 N/mm ²	ASTM D5147 / ASTM D882
Elongation at Break, Longitudinal	≥300 %	ASTM D5147 / ASTM D882
Elongation at Break, Transversal	≥300 %	ASTM D5147 / ASTM D882
Tear Strength, Longitudinal	≥100 N	ASTM D5147
Tear Strength, Transversal	≥80 N	ASTM D5147
Heat Resistance	70OC (No Flow)	ASTM D5147
Low Temperature Flexibility	≤ -10 OC (No Cracks)	ASTM D1970
Puncture Resistance	100 N	ASTM E154
Lap Joint Strength	≥1.8 N/mm	ASTM D1000
Water Absorption @ 24 Hours	≤0.30 % by Weight	ASTM D570
Water Vapor Transmission	≤0.50 g/m ² /24 hrs.	ASTM E96
Softening Point of Coating Compound	≥100 OC	ASTM D36

Application Instruction

Surface Preparation:

The surface receiving waterproofing treatment shall be dry with moisture content <4% and thoroughly cleaned to remove dirt, dust, grease, oil, foreign substances etc., using appropriate tools and methods.

It is recommended to prime the surface using a bituminous primer **Bitucoat Primer** @ 4 to 6 m²/ltr., prior to installation of membrane. Primer should be dry before the application of the membrane. Drying time depends on ambient temperature and humidity.

Application:

The membrane is bonded completely to the primed surface by peeling-off the release film from the membrane bottom and pressing it against the surface using suitable roller.

SELF-ADHESIVE SBS MEMBRANE

Side overlap of at least 75mm and end overlap of at least 100 mm should be maintained properly at the time of application, the overlap sealed by pressing it against the surface using suitable roller.

Limitation

Aquaproof SBS membrane should not be applied when temperature is below +10°C. The membrane after application should not be left exposed to sun for extended period to prevent U.V. rays damage. On vertical surface, the membrane after installation should be protected immediately after application, with HDPE dimple boards. On horizontal surface, the membrane after installation should be protected immediately with 50mm cement-sand screed.

Storage & shelf life

Store in a dry place under the covered shed and protected from rain, sun, heat, U.V rays and low temperatures. It must be stored upright.

Safety precautions

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

Packaging

Aquaproof SBS is supplied in standard roll size of 1m x 20m.

Note

All Technical Data Sheets of FIRSTCHOICE SPECIALITY CHEMICALS are updated on regular basis; it is the user's responsibility, to obtain the most recent issue. Field services where provided, does not constitute supervisory responsibility, for additional information contact our local representative.

Disclaimer

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

FIRSTCHOICE SPECIALITY CHEMICALS PRIVATE LIMITED

Factory Address :

Ahmedabad-
Moraiya, Changodar, Bavla Highway, PS:
Changodar, District- Ahmedabad, Gujarat, PIN- 382213.
Singur-
Shyam Business Park, Durgapur Express way, Dist -
Singur, West Bengal, Pin - 712306

Head Office
"SHRACHI TOWERS"
2nd Floor, 686, Anandpur, E. M. Bypass,
Kolkata - 700 107.
www.fcsc.co.in
Toll free no: 3335000230