



FOR INTERNAL  
AND EXTERNAL USE



FASTER INSTALLATION



FASTER INSTALLATION  
WITH LESS MANPOWER

# TILEGLUE 2.0

## TECHNICAL DATA SHEET



SIMPLE AND MASON  
FRIENDLY MATERIAL



BETTER COVERAGE



ECONOMICAL

#### PRODUCT BENEFITS

- Ready to use
- Environmentally safe
- Safe environment, no odour
- Enriched with water-repellent
- Super strong, self-healing, moisture
- resistant coating
- Good for both, External, Glass, Wet
- Tiles and tiles with water-repellent
- water-repellent
- Application friendly
- Safe handling, easy to mix
- Provides optimum coverage



POLYMER MODIFIED SINGLE COMPONENT CEMENTITIOUS ADHESIVE FOR THE INTERIOR FLOOR AND WALL INSTALLATION OF CERAMIC TILES, VITRIFIED TILES AND NATURE STONE WITH MAXIMUM BED THICKNESS OF 12 MM.





## FEATURES AND BENEFITS

1. Suitable for Interior floor and wall, Polymer modified adhesive
2. Ready to use, consistent quality. Just mix with specified water ratio
3. Self-curing - No curing required, enriched with water retention technology
4. Faster installation with less man power- saves time and labour
5. Better open time, adjustable time, pot life
6. Economical and provides good coverage
7. Anti-Slip properties for the vertical applications



## INSTALLATION TYPES

### Substrate

1. Concrete
2. Concrete & Brick  
Masonry
3. Cement Mortar Beds
4. Cement Plaster/Screed
5. Existing Ceramic and Vitrified tiles
6. Existing Natural stones
7. Cement Terrazzo
8. Light weight blocks



## CERTIFICATION

1. EN 12004- C2T
2. IS 15477:2019 - Type 2 T
3. ANSI 118.4 T



## APPLICATION PROCEDURE

**Surface Preparation:** All the surfaces should be clean, dry, free from dust, oil, grease, loose bonded particles, peeling paints, concrete sealers and structurally sound. The surface should be true to the plumb. Uneven or rough surfaces should be made even and smooth with PLASTWELL/FC READYSCREED to provide a better flat finish. Dampen the dry, dusty concrete/masonry and surfaces heated from exposure to sunlight with water, sweep off the excess water if any. Allow 28 days for walls and floor surfaces to cure prior to tiling. Existing tiles must be roughed and cleaned.



## INSTALLATION PROCEDURE

Apply a thin layer of TILEGLUE 2.0 adhesive to the substrate using the straight edge of the trowel. Place the material over the applied thin layer and comb the adhesive with notch side of the trowel. Spread as much adhesive as can be covered with tile in 15 minutes. If the tile/stone size is >1ft x 1ft, back buttering is mandatory to provide full bedding and firm support. It is recommended to use the proper sized notch trowel to ensure the full bedding of the tile/ stone. Place the tile over the applied wet and sticky adhesive and beat it using rubber hammer or mallet to install it under a firm pressure to ensure a good coverage of the adhesive. Periodically, check the adhesive transfer on the back side of the tile by removing the tile. If the adhesive is dried/not sticky(skinned over), remove and replace with fresh material. It is recommended to provide a minimum of 2mm grout joint around the tiles while.



## MIXING PROCEDURE

**Mixing:** Take 5-6 L of clean, potable water per 20kg of TILEGLUE 2.0 adhesive into a clean mixing bowl. Add adhesive powder into the mixing bowl and mix the material by hand or with a slow speed mixer until a smooth, lump-free paste is obtained. Allow the adhesive to slake for 5 minutes. Adjust the consistency of the material accordingly, if necessary. Remix the adhesive prior to the application and apply with the proper sized notch trowel. The paste should be kept away from direct sunlight and heat.



## COVERAGE

### Coverage

Approx 5-6 m<sup>2</sup> or 55-60 Sqft/20kg bag for 3mm thickness (using 6mm notch trowel).

Approx 3.5-4.5 m<sup>2</sup> or 37-48 Sqft/20kg bag for 4mm thickness (using 8mm notch trowel).

Approx 3-3.3 m<sup>2</sup> or 32-37 Sqft/20kg bag for 5mm thickness (using 10mm notch trowel).

Approx 2.5-3 m<sup>2</sup> or 27-32 Sqft/20kg bag for 6mm thickness (using 12mm notch trowel).

Coverage will depend on the trowel notch size, evenness and smoothness of the substrate, type and size of tile and weather conditions.



## TECHNICAL DATA

|           |              |
|-----------|--------------|
| Product   | TILEGLUE 2.0 |
| Color     | GREY/WHITE   |
| Pack Size | 20KG POWDER  |

Application Data at 25±2°C & 60±5% RH

|                            |                                |
|----------------------------|--------------------------------|
| Open Time in minutes*      | 25 Minutes                     |
| Adjustable Time in Minutes | 35 Minutes                     |
| Density at 27°C            | 1600 to 1700 kg/m <sup>3</sup> |
| Pot Life in hours          | 2-3Hours                       |
| Time to light foot traffic | 16-24 Hours                    |
| Application Temperature    | +5°C to +40°C                  |

\*Open time may vary depending up on the site and atmospheric

### EN 12004 C2T

| TEST PARAMETER            | STANDARD REQUIREMENT    | PRODUCT PERFORMANCE |
|---------------------------|-------------------------|---------------------|
| Open Time (EN 1346)       | ≤0.50 N/mm <sup>2</sup> | 0.80 -0.90          |
| Slip Resistance (EN 1308) | ≤0.50 mm                | 0.25-0.35           |

### Tensile Adhesion Strength in

|                              |                          |           |
|------------------------------|--------------------------|-----------|
| Air Curing EN 1348; CI 8.2   | ≥ 1.00 N/mm <sup>2</sup> | 1.10-1.20 |
| Water Curing EN 1348; CI 8.3 | ≥ 1.00 N/mm <sup>2</sup> | 1.05-1.15 |
| Heat Curing EN 1348; CI 8.4  | ≥ 1.00 N/mm <sup>2</sup> | 1.02-1.10 |
| Freeze-thaw EN 1348; CI 8.5  | ≥ 1.00 N/mm <sup>2</sup> | 1.05-1.15 |

### IS 15477:2019 -Type 2/T Tensile Adhesion Strength in N/mm<sup>2</sup>

|                       |                          |           |
|-----------------------|--------------------------|-----------|
| Dry Condition; CI 5.1 | ≥ 1.00 N/mm <sup>2</sup> | 1.10-1.20 |
| Wet Condition; CI 5.1 | ≥ 1.00 N/mm <sup>2</sup> | 1.05-1.15 |

### Shear Adhesion Strength in N/mm<sup>2</sup>

|                       |                          |            |
|-----------------------|--------------------------|------------|
| Dry Condition; CI 5.2 | ≥ 1.25 N/mm <sup>2</sup> | 1.45 -1.55 |
| Dry Condition; CI 5.2 | ≥ 1.25 N/mm <sup>2</sup> | 1.10-1.20  |
| Wet Condition; CI 5.2 | ≥ 1.25 N/mm <sup>2</sup> | 1.20 -1.30 |

### Slip Resistance

|                         |          |           |
|-------------------------|----------|-----------|
| Slip Resistance; CI 5.5 | ≥0.50 mm | 0.25-0.35 |
|-------------------------|----------|-----------|



## PRECAUTION

---

Although TILEGLUE 2.0 is non-hazardous material, as it contains Portland Cement one should take the following precautions should be taken:

- It is recommended to use the N95 nose mask, gloves and goggles while handling the material
- Keep out of reach of the children
- In case of contact with eyes, rinse your eyes with plenty of water and consult a doctor immediately



## LIMITATION

---

For laying tiles on floor, surface should be structurally sound (28 days curing) & good condition

- Always add powder to water & never add water to powder
- Do not add excess water than recommended
- Never add sand & cement to the mix at site
- Strictly not recommended for tiling on metal, wood, paint and gypsum plaster Do not use for vertical cladding of heavy stone & tiles.

For further and complete information about our product's safe use, please refer to the latest version of our material safety data sheet SHELF LIFE



## GROUTING

---

Grouting can be done after 24 hours of installation for best results.



## CLEANING

---

The tools and containers should be cleaned with plenty of water while the adhesive is still fresh. The surfaces should be cleaned with a damp cloth before the adhesive dries.



## SHELF LIFE

---

12 months from the date of manufacturing in the original unopened manufacturer's packaging.



## STORAGE

---

Store in dry place away from the moisture



## CUSTOMER CARE

For any suggestion or concern, please mail to [support@fcsc.co.in](mailto:support@fcsc.co.in)

For any other product related queries please contact **+91 33 3500 0230**



Scan the QR code to know more about our other products



Office Address :  
"SHRACHI TOWERS"  
3<sup>rd</sup> Floor, 686, Anandpur, E. M. Bypass,  
Kolkata - 700 107.

[www.fcsc.co.in](http://www.fcsc.co.in)  
Helpline no : 3335000230

